

HTD Series Battery

SPACEFLIGHT HTD series battery is Deep Cycle AGM battery designed with thicker plates with more high-density active materials which makes the battery can with stand repeated deep cyclic applications.

Applications

- Solar and wind power systems
- Communication systems
- Uninterruptible power supplies
- Golf carts and buggies
- Alarm and security system
- Electric toy and wheelchairs, etc

General Features

- 5 years designed floating life(25°C)
- Non-spillable construction
- Sealed and maintenance-free
- Excellent recovery from deep discharge
- High density active materials plates
- Longer Life and low self-discharge

Standards

- Compliance with IEC, BS, JIS and EU standards.
- UL, CE Certified
- ISO45001, ISO9001 and ISO14001 certified production facilities


Specifications

Rated Voltage	12V	
Nominal Capacity	7.0Ah	(C ₂₀ , 10.5V)
Approx Weight	2.2kg±3%(4.85lbs)	
Terminal	F1/F2	
Rated Capacity(25°C)	7.0 Ah	(20hr, 0.35A, 10.5V)
	6.6 Ah	(10hr, 0.66A, 10.5V)
	6.0 Ah	(5hr, 1.2A, 10.5V)
	4.3 Ah	(1hr, 4.3A, 9.6V)
Max. Discharge Current	105A(5s)	
Max. Charge Current	1.75A	
Internal Resistance(25°C)	Approx 25mΩ	
Operating Temp. Range	Discharge	-20~60°C (-4~140°F)
	Charge	-10~50°C (14~122°F)
	Storage	-20~60°C (-4~140°F)
Nominal operating temperature	25±5°C	
Charge Voltage @25°C(77°F)	Cycle Use	Initial Charging Current less than 1.75A. Voltage 14.4V~15.0V at 25°C(77°F)Temp. Coefficient -30mV/°C
	Standby Use	Initial Charging Current less than 1.75A. Voltage 13.5V~13.8V at 25°C(77°F)Temp. Coefficient -20mV/°C
Temperature effects on capacity	40°C (104°F)	103%
	25°C (77°F)	100%
	0°C (32°F)	86%
	-15°C (5°F)	65%
Self Discharge(25°C)	Capacity after 3 months storage	91%
	Capacity after 6 months storage	82%
	Capacity after 12 months storage	65%



Dimensions

unit:mm



Length	151±2mm (5.94 inches)
Width	65±2mm (2.56 inches)
Container Height	93±2mm (3.66 inches)
Total Height	99±2mm (3.90 inches)

Battery Construction

Component	Positive plate	Negative plate	Container	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS(UL94-HB) or FR(UL94-V0)	Rubber	Copper	Fiberglass	Sulfuric acid









Constant Current Discharge (Amperes) at 25°C(77°F)

E.V/Time	5min	10min	15min	30min	60min	3h	5h	10h	20h
1.60V	28.0	17.6	14.2	8.00	4.3	1.89	1.26	0.69	0.36
1.65V	26.5	16.8	13.6	7.70	4.2	1.84	1.24	0.68	0.36
1.70V	25.0	16.0	13.0	7.39	4.1	1.80	1.22	0.67	0.35
1.75V	23.5	15.2	12.4	7.10	4.0	1.74	1.20	0.66	0.35
1.80V	22.1	14.4	11.8	6.83	3.9	1.68	1.18	0.65	0.34

Constant Power Discharge (Watts/cell) at 25°C(77°F)

E.V/Time	5min	10min	15min	30min	45min	60min	2h	3h	5h
1.60V	50.7	34.7	27.2	15.0	11.4	8.8	5.02	3.56	2.30
1.65V	49.2	33.0	26.1	14.4	10.8	8.4	4.89	3.47	2.26
1.70V	46.6	31.1	25.0	13.9	10.3	8.0	4.77	3.38	2.22
1.75V	44.1	29.3	24.1	13.3	9.9	7.6	4.62	3.28	2.18
1.80V	41.4	27.7	23.0	12.8	9.6	7.31	4.47	3.17	2.12

Note: The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum.



Factory address: Fukang Industrial Zone, Longnan, Ganzhou, Jiangxi Province, China.
 Shenzhen Office: RM208-210, Building D, Tongju industrial Park, No.4, Longping West Road, Longgang District, Shenzhen.
 TEL: +86-755-28288189 sales@sfbattery.com www.sfbattery.com