

HT Series General Battery

HT8-2(2V8Ah)

Spaceflight HT Series VRLA batteries are designed with AGM technology, high performance plates and technology to give extra power output for common power backup system. HT series batteries are the general purpose with 5-8 years floating design life at 25°C

Applications

- Uninterruptible Power Supply (UPS)
- Emergency backup power supply
- Auto control system
- Communication power supply
- Alarm and security system
- Electric Power System (EPS)

General Features


- 5-8 years design life(25°C)
- Non-spillable construction
- Sealed and maintenance-free
- High reliability and stability
- High purity raw material: long life and low self-discharge

Standards

- Compliance with IEC, BS, JIS and EU standards.
- UL, CE Certified
- ISO45001,ISO9001 and ISO14001 certified production facilities


Specifications

Rated Voltage	2V	
Nominal Capacity	8Ah	(C ₂₀ , 1.75V)
Approx Weight	0.35kg±3%(0.77lbs)	
Terminal	F1	
Rated Capacity(25°C)	8.0 Ah	(20hr,0.4A,1.75V)
	7.7 Ah	(10hr,0.77A,1.75V)
	7.2 Ah	(5hr,1.44A,1.75V)
	5.2 Ah	(1hr,5.2A,1.6V)
Max.Discharge Current	120A(5s)	
Max.Charge Current	2A	
Internal Resistance(25°C)	Approx 6mΩ	
Operating Temp.Range	Discharge	-20~60°C(-4~140°F)
	Charge	-10~50°C(14~122°F)
	Storage	-20~60°C(-4~140°F)
Nominal operating temperature	25±5°C	
Charge Voltage @25°C(77°F)	Cycle Use	Initial Charging Current less than 2A. Voltage 2.4V~2.5V at 25°C(77°F)Temp. Coefficient -30mV/°C
	Standby Use	Initial Charging Current less than 2A. Voltage 2.25V~2.3V at 25°C(77°F)Temp. Coefficient -20mV/°C
Temperature effects on capacity	40°C (104°F)	103%
	25°C (77°F)	100%
	0°C (32°F)	86%
	-15°C (5°F)	65%
Self Discharge(25°C)	Capacity after 3 months storage	91%
	Capacity after 6 months storage	82%
	Capacity after 12 months storage	65%



Dimensions

unit:mm



Diameter	45±2mm (1.77 inches)
Container Height	101±2mm (3.98 inches)
Total Height	110±2mm (4.33 inches)

Battery Construction

Component	Positive plate	Negative plate	Container	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS(UL94-HB) or FR(UL94-V0)	Rubber	Copper	Fiberglass	Sulfuric acid

Constant Current Discharge (Amperes) at 25°C(77°F)

E.V/Time	5min	10min	15min	30min	60min	3h	5h	10h	20h
1.60V	31.00	20.50	14.80	9.00	5.20	2.20	1.50	0.80	0.42
1.65V	30.20	20.00	14.50	8.75	5.10	2.15	1.48	0.79	0.41
1.70V	29.40	19.50	14.20	8.50	5.00	2.10	1.46	0.78	0.41
1.75V	28.60	19.00	13.90	8.25	4.90	2.05	1.44	0.77	0.40
1.80V	27.60	18.30	13.50	7.95	4.75	1.98	1.41	0.75	0.38

Constant Power Discharge (Watts/cell) at 25°C(77°F)

E.V/Time	5min	10min	15min	30min	45min	60min	2h	3h	5h
1.60V	68.3	43.3	31.7	18.7	13.8	11.0	6.00	4.24	2.78
1.65V	66.1	42.2	31.0	18.1	13.5	10.7	5.93	4.20	2.76
1.70V	64.8	40.8	30.1	17.4	13.0	10.4	5.80	4.12	2.73
1.75V	62.3	39.3	29.2	16.5	12.3	9.9	5.66	4.00	2.70
1.80V	59.1	37.5	27.4	15.4	11.6	9.3	5.51	3.85	2.60

Note: The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum.

