SPACEFLIGHT POWER SUPPLY CO., LTD.

HT80-12HX(12V80Ah)

HT Series General Battery

Spaceflight HT Series VRLA batteries are designed with AGM technology, high performance plates and technology to give extra power output for common power backup system. HT series batteries are the general purpose with 5-8 years floating design life at 25°C

Applications

- Uninterruptible Power Supply (UPS)
- Emergency backup power supply
- Auto control system
- Communication power supply
- Alarm and security system
- Electric Power System (EPS)

General Features

- 10-12 years design life(25℃)
- Non-spillable construction
- Sealed and maintenance-free
- High reliability and stability
- High purity raw material: long life and low self-discharge

Standards

- Compliance with IEC, BS, JIS and EU standards.
- UL, CE Certified
- ISO45001,ISO9001 and ISO14001 certified production facilities

Specifications

Rated Voltage		12V
Nominal Capacity	80Ah	(C_{20},10.8V)
Approx Weight		23kg±3%(50.7lbs)
Terminal		F11
Rated Capacity(25℃)	80 Ah 76 Ah 67.5 Ah 54 Ah	(20hr,4A,10.8V) (10hr,7.6A,10.8V) (5hr,13.5A,10.5V) (1hr,54A,9.6V)
Max.Discharge Current		800A(5s)
Max.Charge Current		20A
Internal Resistance(25℃)		Approx 5mΩ
Operating Temp.Range	Discharge Charge Storage	-20~60℃(-4~140℉) -10~50℃(14~122℉) -20~60℃(-4~140℉)
Nominal operating temperature		25±-5℃
Charge Voltage @25℃(77℉)	Cycle Use	Initial Charging Current less than 20A. Voltage 14.4V~15.0V at 25℃(77℉)Temp. Coefficient -30mV/℃
	Standby Use	Initial Charging Current less than 20A. Voltage 13.5V~13.8V at 25℃(77℉)Temp. Coefficient -20mV/℃
Temperature effects on capacity	40℃ (104℉) 25℃ (77℉) 0℃ (32℉) -15℃ (5℉)	103% 100% 86% 65%
Self Discharge(25℃)	Capacity after 3 months storage Capacity after 6 months storage Capacity after 12 months storage	91% 82% 65%

Dimensions unit:mm



Length	350±2mm (13.78 inches)
Width	167±2mm (6.57 inches)
Container Height	179±2mm (7.05 inches)
Total Height	179±2mm (7.05 inches)

Battery Construction

Component	Positive plate	Negative plate	Container	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS(UL94-HB) or FR(UL94-V0)	Rubber	Copper	Fiberglass	Sulfuric acid

Constant Current Discharge (Amperes) at 25℃(77℉)

E.V/Time	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	/	202	160	96.0	54.0	22.3	14.9	8.1	4.25
1.65V	/	193	153	92.0	52.7	21.7	14.5	8.0	4.20
1.70V	/	183	145	87.0	51.2	21.0	14.0	7.9	4.15
1.75V	/	173	137	82.0	49.5	20.3	13.5	7.8	4.10
1.80V	/	160	127	76.0	47.0	19.5	12.9	7.6	4.00

Constant Power Discharge (Watts/cell) at 25℃(77℉)

E.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	/	370	291	181	133	104.5	60.2	42.9	28.2
1.65V	/	356	280	175	130	103.0	59.0	42.0	27.8
1.70V	/	338	268	168	126	101.0	57.7	41.0	27.2
1.75V	/	320	256	161	122	98.5	56.2	40.0	26.8
1.80V	/	300	241	153	117	95.5	54.4	38.8	26.8

Note: The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum.

SPACEFLIGHT POWER SUPPLY CO., LTD.

非凡电源 REMARKABLE ENERGY

HT80-12HX(12V80Ah)

Discharge characteristic



Cycle life in relation to depth of discharge



Charge characteristic curve



Storage Characteristics



Temperature effects on capacity



Temperature effects on float life



Relationship between charging voltage and temperature



Life characteristic of standby use



Factory address: Fukang Industrial Zone, Longnan, Ganzhou, Jiangxi Province, China.
Shenzhen Office: RM208-210, Building D, Tongju industrial Park, No.4, Longping WestRoad,Longgang District,Shenzhen.
TEL:+86-755-28288189 **sales@sfbattery.com** **www.sfbattery.com**